

PCP-9652

DESCRIPTION

The PCP-9652 is a pre-promoted, hybrid, low viscosity, unsaturated polyester resins.

FEATURES AND BENEFITS

- Good wet out properties
- Short cycles of production.
- Quick release of bubble in matrix.

APPLICATIONS

- Polymer concrete.

TYPICAL LIQUID PROPERTIES

Property	Units	Min.	Max.	Test Method
Acid number (solution)	Mg KOH/g sample		35 max	TARQ-100
Non-volatile content	%	60	62	TARQ-204
Brookfield viscosity ²	Cps	90	120	TARQ-300
Gel Time ¹	Minutes	12	16	TARQ-400
Cure Time	Minutes	19	25	TARQ-400
Exothermic Peak	°C	155	175	TARQ-400
Appearance	—	Opalescent		Visual
Stability at 120°C	Hours	1.5	—	TARQ-660

¹1.5% Butanox M-50a @ 25°C; ² LVDVE, spindle #2, 60 rpm @25°C

NOTE: Tests results compared with the reported in certificate can be affected due to: batch age, temperature, moisture, type and amount of catalyst, testing equipment and method.

RECOMMENDATIONS

1. The catalyst level should not exceed 2.8% or fall below 1% for proper cure.
2. These products should not be used when temperature conditions are below 16°C, as curing and handling may be adversely affected.
3. Do not add any material different to the catalyst recommended for these products.
4. Do not mix organic peroxides with metallic soaps, amines or any type of accelerators or promoters, because it can result in a violent decomposition with fire or explosion.
5. Any additional questions, please contact your Reacciones Químicas SA de CV sales representative.

STORAGE

Uncatalyzed PCP-9652 resin, have a usage life of three months from invoice date, when stored at 25°C or below, in a closed, opaque, factory sealed container, out of direct sunlight, heat sources or moisture. For every 7°C increase in storage temperature, the shelf life is reduced by one half.

SAFETY AND HANDLING

Detailed information on the safe handling of the PCP-9652 can be found on its SDS. For more information, please contact your Reacciones Químicas SA de CV sales representative.

DISCLAIMER AND LIMITATION OF LIABILITY

To the best of our knowledge, the information contained herein is accurate. The products sold hereunder shall meet Seller's applicable specifications at time of shipment. Seller's specifications may be subject to change at any time without notice to Buyer. Buyer must give Seller notice in writing of any alleged defect covered by warranty (together with all identifying details, including the product code(s), description and date of purchase) within thirty (30) days of the date of shipment of the product or prior to the expiration of the shipment's quality life, whichever comes first. **THE WARRANTY DESCRIBED HEREIN SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF.** The Buyer's sole and exclusive remedy against Seller shall be for the replacement of the product or refund of the purchase price in the event that a defective condition of the product should be found to exist by the Seller. **NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER.** The sole purpose of this exclusive remedy shall be provided Buyer with replacement of the product or refund of the purchase price of the product if any defect in material or workmanship is found to exist. This exclusive remedy shall not be deemed to have failed its essential purpose so long as Seller is willing and able to replace the defective products or refund the purchase price. Final determination of the suitability of the mater